

PLEXIGLAS® Mineral

PLEXIGLAS® Mineral BV

Product

PLEXIGLAS® Mineral BV is a new generation of mineral materials. The patented product PLEXIGLAS® Mineral BV (a combination of acrylic resin and mineral filler) offers unique thermoforming properties combined with a finished satin or gloss surface, in very large sizes. Like no other material before, PLEXIGLAS® Mineral BV unites the benefits of this class of material with the flexibility of PLEXIGLAS®.

Properties

- 2D thermoforming at very narrow radii
- 3D vacuum thermoforming possible
- Can be seamlessly bonded
- “ready to install” surface
- Large sheet sizes
- Wide selection of thicknesses
- Available in customer colors
- Improved chemical resistance
- Very high resistance to weathering and light
- Water-resistant
- Printable
- Easy-to-clean surface

Application

Owing to these properties, PLEXIGLAS® Mineral BV is suitable for both horizontal and vertical applications in indoor and outdoor areas.

Indoors

- Wall panels/wall protection
- Wet rooms: bathrooms and spas
- Shelves, window sills, furniture
- Sanitaryware such as bathtubs and shower solutions, washstands
- Displays, signs
- Platforms

Outdoors

- Facades/wall paneling
- Window sill and decor profiles
- Objects of all kinds

Processing

PLEXIGLAS® Mineral BV can be machined with all conventional woodworking and plastics processing machines. Carbide or diamond-tipped tools for optimized machining are available on the market.

- PLEXIGLAS® Mineral
Guidelines for Workshop Practice

Available formats

PLEXIGLAS® Mineral BV sheet sizes
3,050 x 2,030 mm (all thicknesses)
4,050 x 2,030 mm (12mm, 10mm on request)

Standard thicknesses: 6, 8, 10, 12mm
Special thicknesses: > 15mm on request

Physical properties

Typical values at 23°C and 50% RH

Mechanical	Values	Unit	Test standard
Flexural modulus of elasticity	min. 4700	MPa	ISO 178
Flexural strength	min. 78	MPa	ISO 178
Elongation at break	max. 2,1	%	ISO 527-2/1B/5
Tensile strength	min. 40	MPa	ISO 527-2/1B/5
Impact stress large ball	> 1800	mm	EN 483-2
Density	1,54	g/cm ³	ISO 1183
Area weight	12,32	kg/m ²	at 8mm thickness
Thickness tolerances to ISO 19712	+/- 1,0 +/- 0,8 +/- 1,0 +/- 1,2	mm mm mm mm	at 6mm thickness at 8mm thickness at 10mm thickness at 12mm thickness
Charpy notched impact strength	1,1	kJ/m ²	ISO 179/1eA
Abrasion, Taber Abraser	145-160	mg	DIN 14688/2006
Barcol hardness	50-70		DIN EN 59
Anti-slip	Class C		DIN 51097
Longitudinal distortion	≤ 1,9	mm/m	Internal
Crosswise distortion	≤ 1,9	mm/m	Internal

Physical properties

Typical values at 23°C and 50% RH

Thermal	Values	Unit	Test standard
Fire behavior	E		DIN EN 13501-1
Fire behavior	B2		DIN 4102 Part 1
Coefficient of linear thermal expansion	50 x 10 ⁻⁶ 0.5 mm/m/10°K	1/K	DIN 53752-A
Heat deflection temperature HDT	100-108	°C	ISO 75
Vicat softening temperature	> 105	°C	ISO 306/B50
Forming temperature (2D)	min. 140	°C	
Forming temperature (3D)	160-210	°C	
Min. bending radius for thermoforming	twice	sheet thickness	internal
Resistance to thermal cycling (hot/cold water)	No cracks, no crazing, no detachment		prEN 14688: 2003
Resistance to thermal cycling (hot/cold water)	no cracks, no crazing, no detachment		ISO 19712

® = registered trademark PLEXIGLAS is a registered trademark of Evonik Röhm GmbH, Darmstadt, Germany.
Certified to DIN EN ISO 9001 (Quality) and DIN EN ISO 14001 (Environment)

Evonik is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Performance Materials GmbH

Acrylic Polymers

Kirschenallee, 64293 Darmstadt, Germany
plexiglas-mineral@evonik.com www.plexiglas.net www.evonik.com

Ref. No. 262-2 en July 2015