

## 351

## Polyester Film

**Description**

Metallized polyester film with excellent dimensional stability and good long- term ageing properties. Specially designed for use on computer-cut equipment, surface with top-coat for printing. Available in the colours chrome, matt chrome, chrome brushed and double-sided glossy gold.

**Release paper**

Silicone coated paper on one side, 137 g/m<sup>2</sup>, which provides excellent waste-stripping properties.

**Adhesive**

Solvent polyacrylate, permanent

**Area of use**

For first class, decorative labels, name and technical plates, decoration and moldings, safety stickers as well as cut lettering and symbols. Suitable for screen-printing and UV-offset-printing.

**Technical Data**

<b>Thickness*</b> (without protective paper and adhesive)	23 micron (chrome, matt chrome, double-sided glossy gold) 50 micron (chrome brushed)
<b>Dimensional stability</b> (FINAT TM 14)	adhered to steel, no measurable shrinkage in cross direction, in length 0.1 mm max.
<b>Temperature resistance***</b>	adhered to aluminium, -50°C to +120°C, no variation
<b>Sea water resistance</b> (DIN 50021)	adhered to aluminium, after 100 h/23°C no variation
<b>Resistance to cleaning agents</b>	adhered to aluminium, 8h in suds (0.5% household cleaner at room temperature and at 65°C), no variation
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	12 N/25 mm
<b>Tensile strength</b> (DIN EN ISO 527)	along: min. 200 MPa across: min. 300 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	along: min. 120% across: min. 85%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +8°C
<b>Service life by specialist application</b> under vertical outdoor exposure (normal climate of Central Europe)	2 years, glossy gold 1 year

\* average

\*\* in original packaging, at 20°C and 50% relative humidity

\*\*\* normal climate of Central Europe

**Note**

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.

